

Styrofan[®] 6609 F

Polymer Dispersions for Architectural Coatings



Product description

Styrofan 6609 F is an aqueous dispersion of a styrene butadien copolymer with low viscosity and excellent pigment binding power.

Dispersion type: anionic

Technical data

Solids content	approx. 50 %
pH value	approx. 6.0 – 7.0
Viscosity ¹	approx. 100 – 300 mPa·s
Average particle size	approx. 0.16 µm
MFFT	approx. 22 °C
Specific gravity (dispersion)	approx. 1.02 g/cm ³

¹ DIN EN ISO 3219 (23 °C, 250 1/s)

The exact specifications can be found in the specification data sheet.

Application areas

- Interior paints
- Interior textured finishes
- Interior putties
- Primers

Advantages

- Excellent robustness/colloidal stability
- Perfect cost-performance ratio
- Low base viscosity - ease of pumping
- Saponification resistance and hydrophobicity
- Wet scrub resistance of formulations

BASF SE
Regional Business Unit
Dispersions and Resins Europe
67056 Ludwigshafen, Germany

The data contained in this publication are based on our current knowledge and experience. They do not constitute the agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

Edition: September 2016

This data sheet will be rendered invalid if it is superseded by a later version.

® = registered trademark of BASF SE