

Styrofan[®] D 422

Polymer Dispersions for Construction

Product description	<p>Owing to its wide range of properties, including high elasticity, good pigmentability, adhesion to a wide variety of substrates, very low water absorbency and the forming of a film that acts as a barrier to water vapor, Styrofan[®] D 422 is especially suitable for the manufacture of protective coatings that form a moisture barrier (waterproofing of wet rooms). Highly effective vapor barrier coatings can be produced in both filled and unfilled formulations.</p> <p>Styrofan[®] D 422 is also suitable for the manufacture of products that act as a barrier to evaporation on the surface of fresh concrete (curing compounds).</p>
Chemical nature	Aqueous dispersion of a copolymer of 1,3-butadiene and styrene which contains carboxyl groups

Properties

Physical form liquid

Technical data (not supply specification)	Solids content	DIN EN ISO 3251	~ 50 %
	pH value	DIN ISO 976	~ 8
	Viscosity	DIN EN ISO 3219 (23 °C, 100 1/s)	30 – 150 mPa s
	Glass transition temperature (T _g)		~ – 7 °C
	Minimum filmforming temperature		~ 1 °C

Application

Processing

Standard commercial antifoams can be used to suppress foaming. In general it is sufficient to add 0.3 – 0,5 % e. g. FoamStar® PB 2706 in relation to the quantity of coating material. The amount required must be determined in tests.

To ensure optimum filler compatibility, the dispersion should be stabilized with a sufficient quantity of dispersing agent e. g. Dispex® AA 4135 or Dispex® CX 4320. We recommend adding preservatives to coating materials that contain Styrofan® D 422 to protect them from microbial attack. The suitability and compatibility of such additives must be determined and monitored in tests.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

BASF SE

Dispersions & Resins Europe
67056 Ludwigshafen, Germany
www.basf.com/dispersions