

Product Information

Impact modified extrusion grade, e.g. for loose buffer tubes; flame retardant halogen and antimony free; light colorable

Abbreviated designation according to ISO 1043: PBT-I FR(40)

Physical form and storage

Standard packaging includes the 25-kg-bag, the 1000 kg octabin (octagonal container) or the 1000 kg big bag. Other forms of packaging are possible subject to agreement. All containers are tightly sealed and should be opened only immediately prior to processing. Further precautions for preliminary treatment and drying are described in the processing section of the brochure. The bulk density is about 0,7 to 0,8g/cm³.

Ultradur® can be stored for a longer period of time in dry, well vented rooms without causing problems in processing. Ultradur® should generally have a moisture content of less than 0,04% when being processed.

In order to ensure reliable production, therefore, pre-drying should generally be the rule and the machine should be loaded via a closed conveyor system. Appropriate equipment is commercially available. Pre-drying is also for the addition of batches, e.g. in the case of inhouse pigmentation.

In order to prevent the formation of condensed water, containers stored in unheated rooms must only be opened when they have attained the temperature prevailing in the processing area. This can possibly take a very long time.

Measurements have shown that the interior of a 25-kg bag originally at 5°C had reached the temperature of 20°C in the processing area only after 48 hours.

Product safety

Ultradur® melts are stable at temperatures up to 280°C and do not give rise to hazards due to molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers, however, Ultradur decomposes on exposure to excessive thermal stresses, e.g. when it is overheated or as a result of cleaning by burning off. At temperatures of > 290 °C can be emitted: carbon monoxide, tetrahydrofuran.

Under special fire conditions traces of other toxic substances are possible. Formation of further decomposition and oxidation products depends upon the fire conditions.

When Ultradur® is properly processed and there is adequate suction at the die no risks to health are to be expected.

Further safety information see safety data sheet of individual product.

Safety data sheet could be ask for at the Ultra-Infopoint under tel: 0621/60-78780.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PBT-I FR(40)
Density	ISO 1183	kg/m ³	1310
Viscosity number (solution 0,005 g/ml Phenole/1,2 Dichlorbenzol 1:1)	ISO 307, 1157, 1628	cm ³ /g	125
Water absorption, saturation in water at 23°C	similar to ISO 62	%	0.4
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	0.25
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	223
MVR 250 °C/2.16 kg	ISO 1133	cm ³ /10min	10
Thermal properties			
Deflection temp. 1.8 (HDT A)	ISO 75-1/-2	°C	55
Deflection temp. under load 0.45 MPa (HDT B)	ISO 75-1/-2	°C	135
Flammability			
UL 94 rating (thickness)	UL-94, IEC 60695	class (mm)	V-2 (0.4)
UL 94 rating (thickness)	UL-94, IEC 60695	class (mm)	V-0 (1.6)
GWFI (thickness)	IEC 60695-2-12	°C (mm)	960 (1)
Limiting Oxygen Index (LOI)	ISO 4589-1/-2	%	42.9
Electrical properties			
Relative permittivity (1 MHz)	IEC 62631-2-1	-	3
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	160
Volume resistivity	IEC 62631-3-1	Ohm*m	1E13
Surface resistivity	IEC 62631-3-2	Ohm	1E16
CTI, solution A	IEC 60112	-	600
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	2000
Yield stress	ISO 527-1/-2	MPa	28
Yield strain	ISO 527-1/-2	%	4.5
Strain at break	ISO 527-1/-2	%	20
Charpy unnotched impact strength, 23°C	ISO 179/1eU	kJ/m ²	40
Charpy unnotched impact strength, -30°C	ISO 179/1eU	kJ/m ²	35
Charpy notched impact strength, 23°C	ISO 179/1eA	kJ/m ²	3.5

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) The typical values of preliminary datasheets are not statistically firm.

BASF SE

67056 Ludwigshafen, Germany