

Product Information **Ultramid®**

A3Z3 R01

02/2026

PA66-I



BASF
We create chemistry

Product Information

Injection moulding grade, mean to high impact

Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm³. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA66-I
Density	ISO 1183	kg/m ³	1080
Water absorption, saturation in water at 23°C	similar to ISO 62	%	6.5 - 7.5
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	260
Melt temperature, injection moulding/extrusion	-	°C	280 - 300
Mould temperature, injection moulding	-	°C	70 - 80
Flammability			
Automotive materials (Thickness 1 mm) ³⁾	ISO 3795, FMVSS 302	-	+
Mechanical properties			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	2150 / 870
Yield stress, 50 mm/min	ISO 527-1/-2	MPa	55 / 36
Yield strain, 50 mm/min	ISO 527-1/-2	%	5 / 38
Nominal strain at break, 50 mm/min	ISO 527-1/-2	%	23 / 246
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	N / N
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	N / N
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	70 / 110
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	15 / 15
Thermal properties			
Deflection temp. under load 1.8 MPa (HDT A)	ISO 75-1/-2	°C	60
Electrical properties			dry / cond.
Relative permittivity (1 MHz)	IEC 62631-2-1	-	3.1 / -
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	200 / -
Volume resistivity	IEC 62631-3-1	Ohm*m	1E13 / -

Footnotes

- 1) If product name or properties don't state otherwise.
- 2) The asterisk symbol "*" signifies inapplicable properties.
- 3) + = passed

BASF SE

67056 Ludwigshafen, Germany