

#### Product Information

Injection-molding grade with 25 % glass fibers, halogen- and antimon-free for parts requiring enhanced fire resistance, especially optimized for good hydrolytical stability and increased tracking resistance

#### Physical form and storage

Standard packaging includes the 25-kg-bag, the 1000 kg octabin (octagonal container) or the 1000 kg big bag. Other forms of packaging are possible subject to agreement. All containers are tightly sealed and should be opened only immediately prior to processing. Further precautions for preliminary treatment and drying are described in the processing section of the brochure. The bulk density is about 0,7 to 0,8g/cm<sup>3</sup>.

Ultradur® can be stored for a longer period of time in dry, well vented rooms without causing problems in processing. Ultradur® should generally have a moisture content of less than 0,04% when being processed.

In order to ensure reliable production, therefore, pre-drying should generally be the rule and the machine should be loaded via a closed conveyor system. Appropriate equipment is commercially available. Pre-drying is also for the addition of batches, e.g. in the case of inhouse pigmentation.

In order to prevent the formation of condensed water, containers stored in unheated rooms must only be opened when they have attained the temperature prevailing in the processing area. This can possibly take a very long time.

Measurements have shown that the interior of a 25-kg bag originally at 5°C had reached the temperature of 20°C in the processing area only after 48 hours.

#### Product safety

Ultradur® melts are stable at temperatures up to 280°C and do not give rise to hazards due to molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers, however, Ultradur decomposes on exposure to excessive thermal stresses, e.g. when it is overheated or as a result of cleaning by burning off. At temperatures of > 290 °C can be emitted: carbon monoxide, tetrahydrofuran.

Under special fire conditions traces of other toxic substances are possible. Formation of further decomposition and oxidation products depends upon the fire conditions.

When Ultradur® is properly processed and there is adequate suction at the die no risks to health are to be expected.

Further safety information see safety data sheet of individual product.

Safety data sheet could be ask for at the Ultra-Infopoint under tel: 0621/60-78780.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>Properties</b>			
Polymer abbreviation	-	-	<b>PBT-GF25 FR(53+30)</b>
Density	ISO 1183	kg/m <sup>3</sup>	<b>1580</b>
Viscosity number (solution 0,005 g/ml Phenole/1,2 Dichlorbenzol 1:1)	ISO 307, 1157, 1628	cm <sup>3</sup> /g	<b>110</b>
Water absorption, saturation in water at 23°C	similar to ISO 62	%	<b>0.4</b>
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	<b>0.2</b>
<b>Processing</b>			
Melting temperature, DSC	ISO 11357-1/-3	°C	<b>223</b>
MVR 275 °C/2.16 kg	ISO 1133	cm <sup>3</sup> /10min	<b>10</b>
Melt temperature, injection moulding/extrusion	-	°C	<b>250 - 270</b>
Mould temperature, injection moulding	-	°C	<b>60 - 100</b>
Molding shrinkage, model-housing 1.5 mm	-	%	<b>0.7</b>
Molding shrinkage (parallel)	ISO 294-4	%	<b>0.50</b>
Molding shrinkage (normal)	ISO 294-4	%	<b>1.30</b>
<b>Thermal properties</b>			
Deflection temp. 1.8 (HDT A)	ISO 75-1/-2	°C	<b>210</b>
Deflection temp. under load 0.45 MPa (HDT B)	ISO 75-1/-2	°C	<b>220</b>
Coefficient of linear thermal expansion, longitudinal (23-55)°C	ISO 11359-1/-2	E-6/K	<b>29</b>
Coefficient of linear thermal expansion, transverse (23-55)°C	ISO 11359-1/-2	E-6/K	<b>167</b>
<b>Flammability (UL yellow card see attachment)</b>			
GWFI (thickness)	IEC 60695-2-12	°C (mm)	<b>960 (1.5)</b>
<b>Electrical properties</b>			
Relative permittivity (1 MHz)	IEC 62631-2-1	-	<b>3.9</b>
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	<b>150</b>
Volume resistivity	IEC 62631-3-1	Ohm*m	<b>1E12</b>
Surface resistivity	IEC 62631-3-2	Ohm	<b>1E15</b>
CTI, solution A	IEC 60112	-	<b>600</b>
Electric strength (d = 0.8 mm)	IEC 60243-1	kV/mm	<b>47</b>
<b>Mechanical properties</b>			
Tensile modulus	ISO 527-1/-2	MPa	<b>8700</b>
Stress at break	ISO 527-1/-2	MPa	<b>120</b>
Strain at break	ISO 527-1/-2	%	<b>2.7</b>
Flexural modulus	ISO 178	MPa	<b>8700</b>
Flexural strength	ISO 178	MPa	<b>210</b>
Charpy unnotched impact strength, 23°C	ISO 179/1eU	kJ/m <sup>2</sup>	<b>55</b>
Charpy unnotched impact strength, -30°C	ISO 179/1eU	kJ/m <sup>2</sup>	<b>45</b>
Charpy notched impact strength, 23°C	ISO 179/1eA	kJ/m <sup>2</sup>	<b>7</b>

### Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "\*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany

Component - Plastics

E41871

BASF SE

Performance Materials Europe, PMD/EX - H201, Ludwigshafen 67056 DE

B4450 G5 HR (t)

Polybutylene Terephthalate (PBT) "Ultradur", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec (°C)	RTI Imp (°C)	RTI Str (°C)
ALL	0.40	V-2	1	0	75	75	75
	0.75	V-2	1	0	140	140	140
	1.5	V-0	1	0	140	140	140
	2.0	V-0, 5VA	1	0	140	140	140
	3.0	V-0, 5VA	0	0	140	140	140

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT) kV: 1

Dielectric Strength (kV/mm): 26

Volume Resistivity (10<sup>9</sup>ohm-cm): -

High-Voltage Arc Tracking Rate (HVTR): 0

Surface Resistivity (10<sup>9</sup>ohms/square): -

Dimensional Change (%): -

High Volt, Low Current Arc Resis (D495): 5

(t) - May be followed by the letters LS and a color code indicating laser sensitive coloring.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2002-04-11

© 2025 UL Solutions



Last Revised: 2019-05-13

### IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.40	V-2 (ALL)
			0.75	V-2 (ALL)
			1.5	V-0 (ALL)
			2.0	V-0, 5VA (ALL)
			3.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC AC Dielectric Strength (AC DS)	IEC 60243-1	kV/mm	-	-
IEC DC Dielectric Strength (DC DS)	IEC 60243-2	kV/mm	-	-
IEC Volume Resistivity (VR)	IEC 62631-3-1	10x ohm-m	-	-
IEC Surface Resistivity (SR)	IEC 62631-3-2	10x ohms	-	-
IEC Inclined Plane Tracking (IPT)	IEC 60587	kV	-	-

BASF SE

67056 Ludwigshafen, Germany

# Ultradur® B 4450 G5 HR



We create chemistry

## UL - Yellow Card

IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m2	-	-
ISO Izod Impact	ISO 180	kJ/m2	-	-
ISO Charpy Impact	ISO 179-1	kJ/m2	-	-