

Product description

An impact-modified, carbon fibre reinforced injection moulding grade with reduced surface resistivity. Flame retardance based on red phosphorus for components requiring enhanced toughness and special requirements on electrical properties.

Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm³. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Preliminary Datasheet ³⁾

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA66-I CF15 FR(52)
Density	ISO 1183	kg/m ³	1190
Viscosity number (0.5% in 96 % H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	180
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	260
MVR 300 °C/10 kg	ISO 1133	cm ³ /10min	7
Melt temperature, injection moulding/extrusion	-	°C	280 - 300
Mould temperature, injection moulding	-	°C	80 - 90
Molding shrinkage, model-housing 1.5 mm	-	%	0.4
Molding shrinkage (parallel)	ISO 294-4	%	0.50
Molding shrinkage (normal)	ISO 294-4	%	0.55
Thermal properties			
Deflection temp. 1.8 (HDT A)	ISO 75-1/-2	°C	235
Deflection temp. under load 0.45 MPa (HDT B)	ISO 75-1/-2	°C	255
Temperature limit for high temperatures, 20000 h, related to 50% decrease of tensile strength	IEC 60216	°C	132
Temperature limit for high temperatures, 5000 h, related to 50% decrease of tensile strength	IEC 60216	°C	169
Coeff. of linear therm. expansion 23°C - 55°C (parallel)	ISO 11359-1/-2	E-6/K	14
Coeff. of linear therm. expansion 23°C - 55°C (normal)	ISO 11359-1/-2	E-6/K	130
Flammability			
UL 94 rating (thickness)	UL-94, IEC 60695	class (mm)	V-0 (1.5)
Fire/ignition performance (UL94+HA1+HWI), min. thickness ⁴⁾	UL 746 C	mm	0.75
GWFI (thickness)	IEC 60695-2-12	°C (mm)	960 (1)
Electrical properties			
Surface resistivity	IEC 62631-3-2	Ohm	dry / cond. - / 1E06
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	10000 / 5800
Stress at break	ISO 527-1/-2	MPa	130 / 85
Strain at break	ISO 527-1/-2	%	3.7 / 8
Flexural modulus	ISO 178	MPa	8000 / 5100
Flexural strength	ISO 178	MPa	180 / 120
Charpy unnotched impact strength, 23°C	ISO 179/1eU	kJ/m ²	70 / 80
Charpy unnotched impact strength, -30°C	ISO 179/1eU	kJ/m ²	70 / -
Charpy notched impact strength, 23°C	ISO 179/1eA	kJ/m ²	13 / 20

Footnotes

- 1) If product name or properties don't state otherwise.
- 2) The asterisk symbol "*" signifies inapplicable properties.
- 3) The typical values of preliminary datasheets are not statistically firm.
- 4) For Electrical Insulation/Barrier with close proximity (<0.8 mm) to uninsulated live parts according to UL 746C

BASF SE

67056 Ludwigshafen, Germany

UL - Yellow Card

Component - Plastics

E41871

BASF SE

Performance Materials Europe, PMD/EX - H201, Ludwigshafen 67056 DE

A3XZC3 ESD(f1)

Polyamide 66 (PA66) "Ultramid", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
BK	0.75	HB	1	0	65	65	65
	1.5	V-0	1	0	65	65	65
	2.3	V-0, 5VA	0	0	65	65	65
	3.0	V-0, 5VA	0	0	65	65	65

Comparative Tracking Index (CTI): - Inclined Plane Tracking (IPT) kV: -

Dielectric Strength (kV/mm): - Volume Resistivity (10⁹ohm-cm): -

High-Voltage Arc Tracking Rate (HVTR): - Surface Resistivity (10⁹ohms/square): -

Dimensional Change (%): - High Volt, Low Current Arc Resis (D495): -

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2021-07-12

© 2022 UL LLC



Last Revised: 2021-07-12

IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.75	HB, HB75 (BK)
			1.5	V-0 (BK)
			2.3	V-0, 5VA (BK)
			3.0	V-0, 5VA (BK)
Glow-Wire Flammability (GWF1)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m2	-	-
ISO Izod Impact	ISO 180	kJ/m2	-	-
ISO Charpy Impact	ISO 179-1	kJ/m2	-	-

BASF SE

67056 Ludwigshafen, Germany