

Product Information

Injection molding grade with 25 % glass fibers for parts requiring enhanced fire resistance as well as increased tracking resistance (eg lamp sockets, connectors, power switches, coil formers, housings for control units), without added halogen and antimony.

Physical form and storage

Standard packaging includes the 25-kg-bag, the 1000 kg octabin (octagonal container) or the 1000 kg big bag. Other forms of packaging are possible subject to agreement. All containers are tightly sealed and should be opened only immediately prior to processing. Further precautions for preliminary treatment and drying are described in the processing section of the brochure. The bulk density is about 0,7 to 0,8g/cm³.

Ultradur® can be stored for a longer period of time in dry, well vented rooms without causing problems in processing. Ultradur® should generally have a moisture content of less than 0,04% when being processed.

In order to ensure reliable production, therefore, pre-drying should generally be the rule and the machine should be loaded via a closed conveyor system. Appropriate equipment is commercially available. Pre-drying is also for the addition of batches, e.g. in the case of inhouse pigmentation.

In order to prevent the formation of condensed water, containers stored in unheated rooms must only be opened when they have attained the temperature prevailing in the processing area. This can possibly take a very long time.

Measurements have shown that the interior of a 25-kg bag originally at 5°C had reached the temperature of 20°C in the processing area only after 48 hours.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PBT-GF25 FR(53+30)
Density	ISO 1183	kg/m ³	1600
Viscosity number (solution 0,005 g/ml Phenole/1,2 Dichlorbenzol 1:1)	ISO 307, 1157, 1628	cm ³ /g	100
Water absorption, saturation in water at 23°C	similar to ISO 62	%	0.9
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	0.2
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	223
MVR 275 °C/2.16 kg	ISO 1133	cm ³ /10min	17
Melt temperature, injection moulding/extrusion	-	°C	250 - 280
Mould temperature, injection moulding	-	°C	60 - 100
Molding shrinkage, model-housing 1.5 mm	-	%	0.7
Molding shrinkage (parallel)	ISO 294-4	%	0.50
Molding shrinkage (normal)	ISO 294-4	%	1.30
Thermal properties			
Deflection temp. 1.8 (HDT A)	ISO 75-1/-2	°C	210
Deflection temp. under load 0.45 MPa (HDT B)	ISO 75-1/-2	°C	220
Coefficient of linear thermal expansion, longitudinal (23-55)°C	ISO 11359-1/-2	E-6/K	35
Coefficient of linear thermal expansion, transverse (23-55)°C	ISO 11359-1/-2	E-6/K	118
Flammability (UL yellow card see attachment)			
GWFI (thickness)	IEC 60695-2-12	°C (mm)	960 (1)
GWIT (thickness)	IEC 60695-2-13	°C (mm)	675 (1)
Railway: Hazard level acc. to requ. sets R22 and R23	EN 45545-2	class	HL2 (0,8 - 6mm)
Electrical properties			
Relative permittivity (1 MHz)	IEC 62631-2-1	-	3.8
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	140
Volume resistivity	IEC 62631-3-1	Ohm*m	1E13
Surface resistivity	IEC 62631-3-2	Ohm	1E14
CTI, solution A	IEC 60112	-	600
Electric strength K20/K20, (60*60*1 mm ³)	IEC 60243-1	kV/mm	38
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	10000
Stress at break	ISO 527-1/-2	MPa	110
Strain at break	ISO 527-1/-2	%	2.2
Flexural modulus	ISO 178	MPa	9700
Flexural strength	ISO 178	MPa	180
Charpy unnotched impact strength, 23°C	ISO 179/1eU	kJ/m ²	45
Charpy unnotched impact strength, -30°C	ISO 179/1eU	kJ/m ²	45
Charpy notched impact strength, 23°C	ISO 179/1eA	kJ/m ²	6

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany

UL - Yellow Card

Component - Plastics

E41871

BASF SE

Performance Materials Europe, PMD/EX - H201, Ludwigshafen 67056 DE

B4450 G5 (t), B4450 G5 BMB (t)

Polybutylene Terephthalate (PBT) "Ultradur", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec (°C)	RTI Imp (°C)	RTI Str (°C)
ALL	0.40	V-2	1	0	75	75	75
	0.75	V-2	1	0	140	140	140
	1.5	V-0	1	0	140	140	140
	2.0	V-0, 5VA	1	0	140	140	140
	3.0	V-0, 5VA	0	0	140	140	140

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT) kV: 1

Dielectric Strength (kV/mm): 26

Volume Resistivity (10^xohm-cm): -

High-Voltage Arc Tracking Rate (HVTR): 0

Surface Resistivity (10^xohms/square): -

Dimensional Change (%): -

High Volt, Low Current Arc Resis (D495): 5

(t) - May be followed by the letters LS and a color code indicating laser sensitive coloring.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2002-04-11

© 2026 UL Solutions



Last Revised: 2024-12-23

IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.40	V-2 (ALL)
			0.75	V-2 (ALL)
			1.5	V-0 (ALL)
			2.0	V-0, 5VA (ALL)
			3.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC AC Dielectric Strength (AC DS)	IEC 60243-1	kV/mm	-	-
IEC DC Dielectric Strength (DC DS)	IEC 60243-2	kV/mm	-	-
IEC Volume Resistivity (VR)	IEC 62631-3-1	10x ohm-m	-	-
IEC Surface Resistivity (SR)	IEC 62631-3-2	10x ohms	-	-
IEC Inclined Plane Tracking (IPT)	IEC 60587	kV	-	-

BASF SE

67056 Ludwigshafen, Germany

Ultradur® B 4450 G5



We create chemistry

UL - Yellow Card

IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-