

Product description

A glass fibre reinforced, flame retardant, partially aromatic polyamide for injection molding. Good mechanical properties, low water absorption, high melting point (295°C). High tracking resistance, low tendency to form deposits on electrical contacts, very resistant to electrolytic corrosion, resistant to soldering temperatures, can be electroplated.

Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm³. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Safety instructions

Provide suitable exhaust ventilation at the drying process and in the area surrounding the melt outlet of processing machines.
Closed containers should only be opened in well-ventilated areas.
Ensure thorough ventilation of stores and work areas.

When incorrectly processing an unpleasant odour can be produced, especially when the recommended processing parameters are exceeded.

Check
- Moisture content of pellets
- Melt temperature
- Residence time

When there is a strong odour, immediately check processing parameters, ventilate the area well and recheck moisture content of material. If necessary stop processing and redry the material.

Any short stoppages in production, it is recommended that you inject material into the mould not purge an air shot. Any molten material drooling from the machine nozzle or hot runner nozzles can self-ignite when in open atmosphere. It is therefore advisable to dispose of purgings etc into water containers.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA6T/6-GF25 FR(52)
Density	ISO 1183	kg/m ³	1380
Viscosity number (0.5% in 96% H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	130
Water absorption, saturation in water at 23°C	similar to ISO 62	%	5 - 6
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	1.1 - 1.5
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	295
Melt temperature, injection moulding/extrusion	-	°C	310 - 330
Mould temperature, injection moulding	-	°C	80 - 120
Moulding shrinkage, constrained ³⁾	-	%	0.4
Moulding shrinkage (parallel)	ISO 294-4	%	0.55
Moulding shrinkage (normal)	ISO 294-4	%	1.00
Flammability (UL yellow card see attachment)			
Glow Wire Flammability Index, GWFI at d = 0.75 mm thickness	IEC 60695-2-12	°C	960
Glow Wire Ignition Test, GWIT at d = 0.75 mm thickness	IEC 60695-2-13	°C	775
Oxygen index	ISO 4589-1/-2	%	26
Mechanical properties			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	8300 / 8000
Stress at break	ISO 527-1/-2	MPa	150 / 140
Strain at break	ISO 527-1/-2	%	3 / -
Tensile creep modulus, 1000 h, strain 0.5%, 23°C	ISO 899-1	MPa	* / 6400
Flexural modulus	ISO 178	MPa	7500 / -
Flexural strength	ISO 178	MPa	210 / -
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	70 / 55
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	8 / 7
Izod notched impact strength (23°C)	ISO 180/A	kJ/m ²	9 / 8
Thermal properties			
Deflection temp. under load 1.8 MPa (HDT A)	ISO 75-1/-2	°C	220
Max. service temperature (short cycle operation)	-	°C	270
Temperature index at 50% loss of tensile strength after 5000 h	IEC 60216	°C	150
Temperature index at 50% loss of tensile strength after 20000 h	IEC 60216	°C	125
Coefficient of linear thermal expansion, longitudinal (23-80)°C	ISO 11359-1/-2	E-6/K	24
Coefficient of linear thermal expansion, transverse (23-80)°C	ISO 11359-1/-2	E-6/K	67
Thermal conductivity	DIN 52612-1	W/(m K)	0.31
Specific heat capacity	-	J/(kg*K)	1400
Electrical properties			dry / cond.
Relative permittivity (1 MHz)	IEC 62631-2-1	-	4 / -
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	200 / -
Volume resistivity	IEC 62631-3-1	Ohm*m	1E13 / 1E12
Surface resistivity	IEC 62631-3-2	Ohm	- / 1E14
Comparative tracking index, CTI, test liquid A	IEC 60112	-	600
Electric strength K20/K20, (60*60*1 mm ³)	IEC 60243-1	kV/mm	37 / 33

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) Test box with central gating, dimensions of base (107*47*1,5) mm, processing condition: TM = 320°C (unreinforced) or 330°C (reinforced), TW = 80°C

BASF SE

67056 Ludwigshafen, Germany

UL - Yellow Card

Component - Plastics

E41871

BASF SE

Performance Materials Europe, PMD/EX - H201, Ludwigshafen 67056 DE

KR4365G5

Polyamide 6/6T (PA6/6T) "Ultramid T", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec (°C)	RTI Imp (°C)	RTI Str (°C)
NC	0.37	V-2	3	2	-	-	-
GY	0.75	V-2	2	0	140	100	120
NC, BK	0.75	V-0	2	0	140	100	120
NC, GY, BK	1.5	V-0	1	0	140	105	130
NC	1.5	5VA	1	0	140	105	130
NC, GY, BK	3.0	V-0	1	0	140	110	140

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT) kV: -

Dielectric Strength (kV/mm): 23

Volume Resistivity (10⁹ohm-cm): 14

High-Voltage Arc Tracking Rate (HVTR): 0

Surface Resistivity (10⁹ohms/square): -

Dimensional Change (%): 0

High Volt, Low Current Arc Resis (D495): 5

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1991-03-12

© 2024 UL Solutions



Last Revised: 2010-05-20

IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.37	V-2 (NC)
			0.75	V-2 (GY)
			0.75	V-0 (NC, BK)
			1.5	V-0 (NC, GY, BK)
			1.5	5VA (NC)
			3.0	V-0 (NC, GY, BK)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	0.75	960
			0.75	960
			1.5	960
			1.5	960
			3.0	960
			Glow-Wire Ignition (GWIT)	IEC 60695-2-13
0.75	775			
1.5	825			
1.5	825			
3.0	825			
3.0	825			

BASF SE

67056 Ludwigshafen, Germany

Ultramid® T KR 4365 G5



We create chemistry

UL - Yellow Card

IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC AC Dielectric Strength (AC DS)	IEC 60243-1	kV/mm	-	-
IEC DC Dielectric Strength (DC DS)	IEC 60243-2	kV/mm	-	-
IEC Volume Resistivity (VR)	IEC 62631-3-1	10x ohm-m	-	-
IEC Surface Resistivity (SR)	IEC 62631-3-2	10x ohms	-	-
IEC Inclined Plane Tracking (IPT)	IEC 60587	kV	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-