

# ecovio<sup>®</sup> F2341

## Biodegradable compound for compostable film

® = ecovio and ecoflex are registered trademarks of BASF SE

### Product Description

ecovio<sup>®</sup> F2341 is one of our biodegradable film products. It is basically a compound of our biodegradable, aliphatic-aromatic copolyester ecoflex<sup>®</sup> F and a small amount of polylactic acid (PLA). Due to its outstanding mechanical strength ecovio<sup>®</sup> F2341 offers a great down gauging potential needed for very thin film applications like T-shirt bags, organic waste bags etc. ecovio<sup>®</sup> F2341 does not contain slip agents. ecoflex<sup>®</sup> slip masterbatches have to be used to tailor the sliding properties required for easy processing on film extrusion and film conversion equipment.

ecovio® F2341 exhibits the following properties:

- High melt strength
- Good thermostability up to 230 °C
- Excellent processability on conventional LDPE blown film lines
- Good mechanical properties
- Down gauging to 15 µm possible, typical thicknesses: 20-50 µm
- Good processability on bag making equipment
- Wet strength (e. g. needed in organic waste bag applications)
- Nice white translucent color
- Excellent welding properties
- Printable in 8 colors by flexo printing

ecovio® F2341 exhibits excellent compatibility to ecoflex®, polylactic acid and other biodegradable polymers. The processing of ecovio® F2341 on extrusion lines depends on the formulation, the extrusion technology and processing conditions. Trials are always recommended to assess the quality of the final product. ecoflex® masterbatches have to be used to tailor the slip properties of the final product. Detailed information concerning our ecoflex® masterbatches will be sent on request. According to our experience pre-drying of ecovio® F2341 is not required if the granules are taken from an unopened bag.

**Certification of Compostability and Biodegradability**

ecovio® F2341 is a biodegradable & compostable compound. Available certificates:



Certification body	DIN Certco	TÜV Austria		BPI
Norm/Certification scheme	EN 13432	OK Compost (EN 13432)	OK Compost Home	ASTM D 6400
Certification Number	7W0188	TA8011300577	TA8021300641	890989-27
Certification body	ABA			
Norm/Certification scheme	AS4736 Compostable	AS5810 Home Compostable		
Certification Number	ABAM 10141	ABAP 20045		

**Food Contact Regulation**

Food contact certificates for ecoflex® and ecovio® grades including information about specific limitations and details concerning the food contact status for different regions can be obtained upon request via a local BASF representative or by contacting plastics.safety@basf.com. The suitability of the article for the application concerned must be ensured in each case by the person who places any finished food contact article on the market.

**Form Supplied and Storage**

ecovio® F2341 is supplied as lenticular pellets in 1t big bags. Temperatures during transportation and storage may not exceed 60 °C at any time. Storage time of unopened bags may not surpass 12 month at room temperature (23 °C).

## Quality Control

ecovio® F2341 is produced as a standard material in a continuous production process according to DIN EN ISO 9001. The melt volume rate, MVR, at 190 °C, 5 kg, according to ISO 1133 has been defined as specified parameter for quality control. A certificate can be provided with each lot number upon request. The ecovio® granules have to be pre-dried (6 hours at 70 °C) before MVR measurement in order to obtain accurate values. Other data given in our literature are typical values, which are not part of our product specification for ecovio® F2341.

## Applications

ecovio® F2341 has been developed for the conversion to flexible films using a blown film process. Typical applications are organic waste bags, carrier bags, courier bags. In view of numerous factors influencing functionality and shelf life of ecovio® films and finished articles made thereof the production parameters have to be tested by the converters before utilization. Additionally sufficient field tests are required to ensure the right functionality of the articles made from ecovio® F2341.

We supply technical service information concerning the blown film process with ecovio® F2341 on demand.

## Typical Basic Material Properties of ecovio® F2341

\*see Quality Control

Property	Unit	Test Method	ecovio® F2341
Mass Density	g/cm <sup>3</sup>	ISO 1183	1.36-1.40
Bulk Density	kg/m <sup>3</sup>	DIN EN ISO 60	800
Melt Volume Rate MVR 190°C, 5kg*	ml/10 min.	ISO 1133	5.0-11.0
Melting Points	°C	DSC	110-120
	°C	DSC	140-155

## Typical Properties\* of ecovio® F2341 Blown Film, 25 µm

\*not to be construed as specifications

Property	Unit	Test Method	ecovio® F2341
Tensile Modulus MD/TD	MPa	ISO 527	260/130
Tensile Strength MD/TD	MPa	ISO 527	25/25
Ultimate Elongation MD/TD	%	ISO 527	480/570
Dart Drop	g	ASTM D 1709-04 Method A	250
Tear Resistance MD/TD	mN	DIN EN ISO 6383-2	1600/1300

## Note

The information submitted in this document is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance for a special purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. (January 2023)