

Product description

Ultraform® S2320 003 PRO AT is a free-flowing, rapid-solidifying grade for thin-walled moldings that are difficult to produce by injection molding.

Ultraform® S2320 003 PRO AT has been introduced for medical applications and offers a comprehensive service package with formulation consistency and a management of change process.

Ultraform® S2320 003 PRO AT is suitable for the production of various functional mechanical components, e.g. valves, springs, gears, snap mechanisms, guide and sliding elements for e.g. injection pens and drug delivery devices.

The following statements are available for Ultraform® S2320 003 PRO AT:

Food contact:

- EU 10/2011, FDA 21 CFR §177.2470
- GMP 2023/2006

Medical applications:

- Pharmacopoeias: Europe, Japan
- Biocompatibility: USP Class VI, ISO 10993-5
- DMF 33741

For questions regarding compliance with additional regulations and certificates, please contact your local BASF representative or Plastics Safety (email: plastics.safety@basf.com).

Abbreviated designation according to ISO 1043-1: POM
Designation according to ISO 29988-POM-K,,M-GNR,4-2

Physical form and Storage

Ultraform® is supplied in the form of granules having a bulk density of approx. 850 g/l. Standard packs are 25 kg PE bag and 800 kg Octabin (octagonal container). Ultraform® is not subject to change when it is stored in dry, ventilated rooms. After relatively long storage (>1 year) or when handling material from previously opened containers, preliminary drying is recommended in order to remove any moisture which has been absorbed.

Product safety

Ultraform® is not a hazardous material as defined in the German Ordinance on Hazardous Materials.

If Ultraform® is processed properly little or no formaldehyde occurs in the region of the processing machine. Measures should be taken to ensure ventilation and venting of the work area, preferably by means of an extraction hood over the barrel unit.

Ultraform® decomposes when subjected to excessive heat. The decomposition products formed in this case consist almost exclusively of formaldehyde, a gas which has a pungent smell even at very low concentrations and irritates the mucous membranes. Decomposition can rapidly result in the build-up of a high gas pressure in the barrel of the processing unit. If the die is sealed there may be a sudden release of pressure via the filling hopper.

Contamination of Ultraform® by thermoplastics that cause decomposition of polyacetals, e.g. PVC or plastics containing halogenated fire protection agents, must be avoided under all circumstances. Even small quantities can cause uncontrolled and rapid decomposition of Ultraform® during processing.

If processing with color masterbatches or functional batches is intended, the compatibility of the components must be established by suitable trials. Processing with incompatible masterbatches may result in decomposition and release of gaseous formaldehyde.

Pellets and finished parts must not be allowed to come into contact with strong acids (especially concentrated hydrochloric acid) since they cause Ultraform® to decompose.

Detailed safety and environmental information is contained in the Ultraform® brochure and the material safety data sheet. Both are available from www.plastics.basf.com.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Processing Data Sheet

	Test method	Unit	Values
Properties			
Polymer abbreviation	-	-	POM
Density	ISO 1183	kg/m ³	1410
Melt volume rate MVR 190 °C/2.16 kg	ISO 1133	cm ³ /10min	11
Drying			
Moisture, max.	-	%	0.2
Dryer temperature ¹⁾	-	°C	100
Drying time	-	h	3
Injection molding			
Melt temperature range	-	°C	190 - 230
Melt temperature, optimal	-	°C	200
Mold temperature range	-	°C	60 - 120
Mold temperature, optimal	-	°C	90
Residence time, max.	-	min	10
Machine Settings			
Temperature hopper throat	-	°C	80
Cylinder temperature 1 (feed zone)	-	°C	200
Cylinder temperature 2 (compression)	-	°C	200
Cylinder temperature 3 (metering-zone, in front of the screw)	-	°C	200
Cylinder temperature 4 (nozzle)	-	°C	200
Peripheral screw speed	-	m/s	0.3
Shrinkage			
Molding shrinkage (parallel)	ISO 294-4	%	2.10
Molding shrinkage (normal)	ISO 294-4	%	2.10

Footnotes

1) The granules or pellets in their original packaging can generally be processed without any special preliminary treatment. However, granules or pellets which have become moist due to prolonged or incorrect storage must be dried in suitable dryers, e.g. dehumidifying dryers.