Product Information

Ultramid® Advanced

N4HG7 LS BK23593

09/2026

PA9T-GF35

We create chemistry

Product description

Partially aromatic, glassfiber reinforced polyphthalamide for injection molding with strong mechanical properties especially at elevated temperatures, good long-term thermal stability and outstanding chemical resistance for highly stressed parts. Ultramid® Advanced N4HG7 LS BK 23593 can be characterized as compound with high toughness, stiffness, extremely low water absorption and outstanding dimensional stability. It is based on a high molecular weight polymer, and features exceptional resistance against many challenging media such as automotive coolant fluids. Ultramid® Advanced N4HG7 LS BK 23593 is easily processable with excellent melt stability.

Markets & applications
Automotive: Fuel system, cooling system, powertrain, Auto E&E, sensors, pumps, fuel cell
E&E: Connectors
Consumer goods: Home appliances, consumer electronics

Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm³. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.
In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultramid® Advanced N4HG7 LS BK23593

Product Information

Typical values for uncoloured product at 23 °C[1)]	Test method	Unit	Values[2)]
Properties			
Polymer abbreviation	-	-	**PA9T-GF35**
Density	ISO 1183	kg/m³	**1420**
Viscosity number (0.5% in 96% H_2SO_4)	ISO 307, 1157, 1628	cm³/g	**120**
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	**0.8**
Water absorption, saturation in water at 23°C	similar to ISO 62	%	**1.9**
Water absorption, 24 h in water, 23°C	ISO 62	%	**0.2**
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	**300**
Melt temperature, injection moulding/extrusion	-	°C	**320 - 340**
Mould temperature, injection moulding	-	°C	**125 - 160**
Molding shrinkage (parallel)	ISO 294-4	%	**0.48**
Molding shrinkage (normal)	ISO 294-4	%	**0.88**
Flammability			
UL 94 rating at 0.8 mm thickness	IEC 60695-11-10	class	**HB**
Mechanical properties			**dry / cond.**
Tensile modulus (23°C)	ISO 527-1/-2	MPa	**11500 / 11500**
Stress at break (23°C)	ISO 527-1/-2	MPa	**210 / 190**
Strain at break (23°C)	ISO 527-1/-2	%	**2.5 / 2.3**
Tensile modulus (120°C)	ISO 527-1/-2	MPa	**8500 / -**
Stress at break (120°C)	ISO 527-1/-2	MPa	**120 / 85**
Strain at break (120°C)	ISO 527-1/-2	%	**3.4 / 4.2**
Tensile modulus (170°C)	ISO 527-1/-2	MPa	**5000 / -**
Stress at break (170°C)	ISO 527-1/-2	MPa	**80 / -**
Strain at break (170°C)	ISO 527-1/-2	%	**5 / -**
Flexural modulus (23°C)	ISO 178	MPa	**10500 / 10500**
Flexural strength	ISO 178	MPa	**290 / 265**
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m²	**80 / -**
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m²	**90 / 70**
Charpy impact strength (120°C)	ISO 179/1eU	kJ/m²	**70 / -**
Charpy impact strength (170°C)	ISO 179/1eU	kJ/m²	**70 / -**
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m²	**9 / -**
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m²	**10 / 8**
Charpy notched impact strength (120°C)	ISO 179/1eA	kJ/m²	**15 / -**
Charpy notched impact strength (170°C)	ISO 179/1eA	kJ/m²	**28 / -**
Thermal properties			
Deflection temp. under load 1.8 MPa (HDT A)	ISO 75-1/-2	°C	**270**
Coefficient of linear thermal expansion, longitudinal (23-55)°C	ISO 11359-1/-2	E-6/K	**17 - 18**
Coefficient of linear thermal expansion, transverse (23-55)°C	ISO 11359-1/-2	E-6/K	**56 - 57**
Thermal conductivity, solid material (23°C)	DIN 52612-1	W/(m K)	**0.29**
Specific heat capacity (23°C)	-	J/(kg*K)	**1100**
Electrical properties			**dry / cond.**
Volume resistivity	IEC 62631-3-1	Ohm*m	**>1E16 / >1E14**
Surface resistivity	IEC 62631-3-2	Ohm	**- / >1E14**
Comparative tracking index, CTI, test liquid A	IEC 60112	-	**- / 600**

Footnotes
1) If product name or properties don't state otherwise.
2) The asterisk symbol '*' signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany