

Product description

Heat stabilized, partially aromatic polyphthalamide for injection molding with strong mechanical properties especially at elevated temperatures and excellent chemical resistance for highly stressed parts. The product can be characterized as compound with high strength and stiffness, very low water absorption and outstanding dimensional stability. It features a high melting point (320°C) and excellent melt stability.

Markets & applications

Automotive: Fuel system, cooling system, powertrain, metal replacement, structural parts

Industry goods: Pumps, compressors

Consumer goods: Home appliances

Physical form and storage

The product is supplied in the form of granules with a bulk density of approx. 0.7 g/cm³. Standard packs are bag and bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Other packaging materials and shipping in road or rail silo wagons are possible by agreement. The containers should only be opened immediately before processing or drying. To ensure that the delivered product absorbs as little moisture as possible, the containers should be stored in dry rooms and always carefully closed again after partial quantities have been withdrawn. In principle, the product can be stored for a long period of time. Containers stored in cold rooms should be equalized to ambient temperature before opening in order to avoid condensation on the granules. Regardless of the storage conditions, the product should be pre-dried according to our recommendations and the machine should preferably be loaded using a closed conveyor system.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

Product Information

| Typical values for uncoloured product at 23 °C ¹⁾ | Test method | Unit | Values ²⁾ |
|--|---------------------|--------------------|----------------------|
| Properties | | | |
| Polymer abbreviation | - | - | PA6T/6I GF60 |
| Density | ISO 1183 | kg/m ³ | 1770 |
| Viscosity number (0.5% in 96% H ₂ SO ₄) | ISO 307, 1157, 1628 | cm ³ /g | 95 |
| Processing | | | |
| Melting temperature, DSC | ISO 11357-1/-3 | °C | 320 |
| Melt temperature, injection moulding/extrusion | - | °C | 345 - 355 |
| Mould temperature, injection moulding | - | °C | 150 - 190 |
| Molding shrinkage (parallel) | ISO 294-4 | % | 0.37 |
| Molding shrinkage (normal) | ISO 294-4 | % | 0.64 |
| Test specimen production, injection moulding, melt temp. | ISO 294 | °C | 350 |
| Test specimen production, injection moulding, mould temp. | ISO 294 | °C | 150 |
| Mechanical properties | | | |
| Tensile modulus (23°C) | ISO 527-1/-2 | MPa | 22500 / 22500 |
| Stress at break (23°C) | ISO 527-1/-2 | MPa | 265 / 250 |
| Strain at break (23°C) | ISO 527-1/-2 | % | 1.7 / 1.5 |
| Tensile modulus (80°C) | ISO 527-1/-2 | MPa | 21000 / 21000 |
| Stress at break (80°C) | ISO 527-1/-2 | MPa | 210 / 200 |
| Strain at break (80°C) | ISO 527-1/-2 | % | 1.7 / 1.5 |
| Tensile modulus (120°C) | ISO 527-1/-2 | MPa | 18000 / - |
| Stress at break (120°C) | ISO 527-1/-2 | MPa | 160 / - |
| Strain at break (120°C) | ISO 527-1/-2 | % | 2.4 / - |
| Tensile modulus (170°C) | ISO 527-1/-2 | MPa | 7000 / - |
| Stress at break (170°C) | ISO 527-1/-2 | MPa | 75 / - |
| Bruchdehnung (170°C) | ISO 527-1/-2 | % | 4.5 / - |
| Thermal properties | | | |
| Deflection temp. under load 1.8 MPa (HDT A) | ISO 75-1/-2 | °C | > 280 |
| Thermal conductivity, solid material (40°C) | DIN 52612-1 | W/(m K) | 0.46 |
| Specific heat capacity (23°C) | - | J/(kg*K) | 0.81 |

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany