

# Rheovis<sup>®</sup> HS 1332

**Product description** Rheology modifier

**Key benefits**

- Excellent mid to high-shear thickener (HASE) for aqueous coatings
- High solid content
- Extended Food Contact Compliances
- Improved flow and leveling

**Chemical nature** Aqueous, acrylic polymer emulsion

## Properties

**Physical form** White liquid (emulsion)

**Technical data**

(not supply specification)

Solid content	DIN EN ISO 3251, modified	~ 40 %
Product viscosity	DIN EN ISO 2555	< 50 mPa.s
pH value	DIN ISO 976	~ 3.2

---

## Application

Rheovis® HS 1332 is an excellent rheology-control agent for water-based coatings to increase viscosity in the mid to high-shear range. The polymer provides the rheology-control effect through extensive swelling of the high-molecular-weight polymer in combination with a hydrophobic component. This leads to superior rheology-build and low spattering, ideal for a broad range of matt to semi-gloss interior and exterior coatings. Rheovis® HS 1332 is most effective between pH 8 to 10.

**Formulation guideline** 1.0 - 3.5% on total formulation.

We recommend determining the optimum dosage of Rheovis® HS 1332 by laboratory trials to achieve optimum performance.

Rheovis® HS 1332 can be added at any stage of the production process. Afterwards the pH should be checked again and adjusted to 8-10.

Rheovis® HS 1332 can also be mixed into polymer dispersions in the form of an alkaline solution. The solid content of the solution should not be higher than 1% to ensure easy handling. It is recommended to dilute the thickener with water and add alkaline whilst stirring. Check and adjust the pH afterwards.

Depending on the application, it can be advisable to use Rheovis® HS 1332 in combination with other Rheovis® thickeners or cellulose derivatives to obtain the desired rheological effects.

---

## Storage

Keep container tightly closed and store in a cool, dry place. Protect from temperatures below 5 °C and above 40 °C. If stored at low temperatures, freezing of the product can irreversibly damage the product

### Contacts worldwide

Asia  
BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

### Validity

This Technical Data Sheet is valid for all versions of the Rheovis® HS 1332.

### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)