

Styronal[®] ND 656

Chemical Nature

Aqueous dispersion of a carboxylated styrene/butadiene copolymer used in the formulation of industrial adhesives for combining and laminating

Properties

Typical properties

Solids content	%	~ 50.0
pH value		~ 7.0
Viscosity at 23 °C (Brookfield RV, Spindle #2, at 20 rpm)	cps	~ 50 – 350

Other properties of the dispersion

Density	lbs/gal	ca. 8.3
Bound styrene	%	ca. 66
Residual Styrene	%	0.03 max
Surface tension	nM/m	ca. 38
Average Particle size	microns	ca. 0.15
Dispersion type		anionic

Properties of the film

Glass transition temperature (DSC)	°C	18
Mechanical Strength*		
Tensile strength	psi	ca. 1200
Elongation at break	%	ca. 250
Surface		hard, non-tacky

* These values permit only a rough comparison of film strengths.

Compatible with

Polymer dispersions

Butofan[®] NS 144, NS 166, NS 208, Styrofan[®] ND 593

Thickeners

Collacral[®] VL, Latekoll[®] D and casein solutions

Other Resins

Commercial rosin and hydrocarbon tackifier dispersions

* The above values should not be taken as specification.

Application

Styronal ND 656 is a mechanically and chemically stable dispersion that improves the cohesive strength of laminating adhesives.

Processing

Adding a preservative to adhesives and coating materials that contain Styronal ND 656 is recommended to protect from microbial attack, particularly if the pH lies in a neutral range. The suitability of such additives must be verified and monitored in trials.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Styronal ND 656.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Styronal is a registered trademark of BASF Group.

© BASF Corporation, 2023



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
www.basf.us/dpsolutions